



## DIMPLED SHEET DATA SHEET

### TECHNICAL SPECIFICATIONS

Properties	Standart
Weight	400 g/m <sup>2</sup>
Strength at Break	(MD - CMD) 200 -200 N/5 cm
Elengation at Break	(MD - CMD) %20 - %25 N/5 cm
Compressive Strength	TS EN 826-120 kN/m <sup>2</sup>
Roll Weight	16 / 24 kg
Roll Length	20 or 30 m
Roll Wide	2 m
Thickness	0,55 mm
Stud Hight	8 mm

Properties	Standart
Weight	500 g/m <sup>2</sup>
Strength at Break	(MD - CMD) 250 -250 N/5 cm
Elengation at Break	(MD - CMD) %20 - %25 N/5 cm
Compressive Strength	TS EN 826-200 kN/m <sup>2</sup>
Roll Weight	20 / 30 kg
Roll Length	20 or 30 m
Roll Wide	2 m
Thickness	0,65 mm
Stud Hight	8 mm

Properties	Standart
Weight	600 g/m <sup>2</sup>
Strength at Break	(MD - CMD) 300 -300 N/5 cm
Elengation at Break	(MD - CMD) %20 - %25 N/5 cm
Compressive Strength	TS EN 826-250 kN/m <sup>2</sup>
Roll Weight	24 / 36 kg
Roll Length	20 or 30 m
Roll Wide	2 m
Thickness	0,80 mm
Stud Hight	8 mm

تهران، خ یوسف آباد، خ شهید قدس میرحیدری، پ۶۷، واحد ۱، شرکت آرین خاک ایرانیان

تماس: ۰۲۱۸۸۰۰۵۰۴۳ فکس: ۰۲۱۸۹۷۷۰۸۲۷